

Technical Datasheet



AROPOL™ M 604 TB Low Styrene Content Resin / Vapour Suppressed

AROPOL M 604 TB is a vapour suppressed, low styrene content DCPD based polyester resin. The resin is pre-accelerated and thixotropic.

Low styrene emission, good glass fiber wet out, low shrinkage and good surface cosmetics are characteristic for AROPOL M 604 TB resin.

Typical liquid resin properties

Property at 23 °C	Value	Unit	Method
Viscosity, Brookfield RV2, 10 rpm	1200	mPas	ISO 2555
Viscosity, cone&plate	180	mPas	ISO 2884
Styrene content	37	%	SFS 4864
Geltime, 1% MEKP-50	35	min	D 006
Peak exotherm	120	°C	D 006

Typical cured resin properties

Property	Value	Unit	Method
Tensile strength	45	MPa	ISO 527
Tensile modulus	3100	MPa	ISO 527
Elongation at break	1,6	%	ISO 527
Heat deflection temperature (ultimate)	85	°C	ISO 75/2 (A)
Hardness	40	Barcol	ASTM D2583
Water absorption, 28 days	76	mg/sample*	ISO 62-80

* sample 50x50x4 mm

Application and use

AROPOL M 604 TB resin is developed for spray-up and hand lay-up applications and suitable for manufacturing of products for the marine, transportation and building and construction markets.

Certificate and approvals

The manufacturing, quality control and distribution of products, by Ashland Performance Materials, are complying with one or more of the following programs or standards: Responsible Care, ISO 9001, ISO 14001 or OHSAS 18001.

Handling and storage

It is highly recommended that all material is stored at stable temperatures under 20 °C preferably indoors, and away from direct sunlight. Prolonged storage or storage outside of recommended conditions can influence liquid resin properties like viscosity and geltime. It is also strongly recommended to mix resin thoroughly before use. Shelf life of AROPOL M 604 TB is three (3) months.



Responsible Care*

* Registered service mark of the American Chemistry Council. © Registered trademark and ™ trademark of Ashland Inc.

Ashland is committed to the continuous evolution of technology and service solutions that promote health, safety and environmental protection around the world.

Technical Datasheet



AROPOL™ M 604 TB Low Styrene Content Resin / Vapour Suppressed

Notice

All information presented herein is believed to be accurate and reliable, and is solely for the user's consideration, investigation and verification. The information is not to be taken as an express or implied representation or warranty for which Ashland assumes legal responsibility. Any warranties, including warranties of merchantability, fitness for use or non-infringement of intellectual property rights of third parties, are herewith expressly excluded.

Since the user's product formulations, specific use applications and conditions of use are beyond the control of Ashland, Ashland makes no warranty or representation regarding the results which may be obtained by the user. It shall be the sole responsibility of the user to determine the suitability of any of the products mentioned for the user's specific application.

Ashland requests that the user reads, understands and complies with the information contained herein and the current Material Safety Data Sheet.



Responsible Care*

* Registered service mark of the American Chemistry Council. © Registered trademark and ™ trademark of Ashland Inc.

Ashland is committed to the continuous evolution of technology and service solutions that promote health, safety and environmental protection around the world.