

ADDpoxy® 1001-X-75

Medium molecular weight Epoxy Resin solution

- General** ADDpoxy® 1001-X-75 is a medium molecular weight epoxy resin based on Bisphenol A as solvent cut 75% in Xylene.
- Applications** ADDpoxy® 1001-X-75 may be used as modifier in oil-free polyester or acrylic resin system to improve the mechanical and electrical properties of such coatings. The resin solution also can be used for higher solids type -1 resin systems cured with polyamidoamines for highly filled coatings for marine maintenance and protective coatings applications.
- Properties** ADDpoxy® 1001-X-75 formulated coatings give,
- Excellent adhesion
 - Good mechanical properties
 - Moderate to good resistance to chemicals
 - Good salt water resistant
 - Good corrosion resistance
 - Due to lower molecular weight of ADDpoxy® 1001-X-75 the compatibility with insoluble, acrylics and alkyd-amino combinations is improved, compared to similar grade epoxies.

Specific Key Data	Property	Value	Test method
	Appearance	Clear, no contamination	JCTM 003
	Color (Gardner)	3 max	ASTM D-1544
	Epoxy Value (supplied)	1.42 - 1.67 eq/Kg	ASTM D-1652
	Weight per Epoxide (supplied)	600 - 700 g/eq	ASTM D-1652
	Solid Content	74 - 76%	JCTM 0097
	Viscosity at 25°C (77°F)	5000 - 10000 mPas	ISO 12058-1

Specific key data are individually checked throughout, guaranteed and included in certificate of analysis.

Typical Key Data	Property	Value	Test method
	Density at 25°C ~	1.08 g/cm ³	ISO 1675
	Flash point, closed cup	31 °C	DIN 53213

Typical key data are spot-checked; the values are typical for the product and are indicated for information only. The values are not included in certificate of analysis.

As-supplied form	Liquid
Odor	Yes (Xylene)
Shelf life (at storage temperature between 2-40°C) (See expiry date on original container)	Several years
Hazardous decomposition products (When disposed of in fire)	Carbon monoxide, carbon dioxide and other toxic gases and vapors.
Disposal	Regular procedures approved by local authorities.

Packaging and Storage ADDpoxy® 1001-X-75 is supplied in bulk and in steel drums containing 210 Kgs. This product should be stored in a dry place, preferably in the sealed original containers, at temperatures between 2 and 40°C. The products should not be stored exposed to direct sunlight.

**Handling/Safety
Precautions**

Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product safety data sheets.

Note

ADDpoxy® is a registered trademark of JANA or an affiliate thereof.

Jubail Chemical Industries Co. (JANA)
P.O Box 11919
Jubail Industrial city 31961
Kingdom of Saudi Arabia
Tel : +966 3 3478888
Fax : +966 3 3476705

DISCLAIMER:

THE INFORMATION AND RECOMMENDATIONS CONTAINED HEREIN ARE BASED UPON OUR DATA BELIEVED TO BE CORRECT. HOWEVER, SINCE THE CONDITIONS OF USE ARE BEYOND OUR CONTROL, NO GUARANTEE OR WARRANTY OF ANY KIND, EXPRESSED OR IMPLIED IS MADE WITH RESPECT TO THE INFORMATION CONTAINED HEREIN.

**ADD RESINS BRANCHES AT:
JOHANNESBURG / DURBAN / CAPE TOWN**

addresins.com